



**WHEN IT COMES TO JOBSITE SAFETY,
YOUR WORKERS DESERVE THE BEST...**



SCAFFOLD BOARDS

THE NATURAL CHOICE FOR SAFETY!

* * * * *

PROOF-TESTED

CAN/CSA-S269.2-M87 COMPLIANT

MEETS OSHA & ANSI STANDARDS

STAMPED AS "SCAFFOLD PLANK"

PREDICTABLE STRENGTH

LIGHTEST IN WEIGHT

VARIETY OF SIZES & LENGTHS

READILY AVAILABLE

* * * * *



MASTER PLANK® is Produced by Finforest USA, Engineered Wood Division
Copyright © 2003 McCausey Lumber Co. All rights reserved.

SIA

Member - Scaffold Industry Association



SCAFFOLD BOARDS

WHY ARE **MASTER PLANK** LAMINATED SCAFFOLD BOARDS THE PLANK OF CHOICE?

MASTER PLANK is an engineered wood product designed specifically for use as a scaffold board. The unique process by which it is manufactured disperses the inherent defects found in solid-sawn lumber. Natural characteristics such as knots and wane are rearranged to maximize strength and minimize warping and splits.

MASTER PLANK is homogeneous and has superior strength properties.

MASTER PLANK is proof-tested to ensure compliance to the OSHA & ANSI A10.8-2001 & CAN/CSA-S269.2-M87 Standards and is stamped accordingly.

MASTER PLANK is manufactured from spruce veneers, making it the lightest weight laminated wood scaffold plank on the market.

MASTER PLANK is remarkably durable due to its use of critically selected spruce veneers and waterproof exterior adhesive.

MASTER PLANK is manufactured under the ISO 9001 Quality Certification System and is inspected under the guidance of an independent nationally recognized inspection agency.

MASTER PLANK is manufactured from forests managed and certified according to the ISO 14001 environmental standard and the ISO 9002 quality standard.



Standard Sizes			
Thickness	Width	Length	Weight (plf)
1 1/2"	9 1/4"	8-24'	3.2
	11 3/4"	8-24'	3.9
1 3/4"	9 1/2"	8-24'	3.6
	11 3/4"	8-24'	4.5

Note: Other thicknesses, widths and lengths are available on a custom order basis.

MASTER PLANK IT'S NOT JUST ANY SCAFFOLD BOARD


MASTER PLANK SCAFFOLD BOARD SPAN TABLES (CANADA)

One Span (Simple) L/80	Dry Use (<19% Moisture Content)			Wet Use (>19% Moisture Content)		
	1-1/2"x9-1/4"	1-3/4"x9-1/2"	1-3/4"x11-3/4"	1-1/2"x9-1/4"	1-3/4"x9-1/2"	1-3/4"x11-3/4"
50 psf	9' - 6"	11' - 6"	11' - 6"	9' - 0"	10' - 6"	10' - 6"
75 psf	8' - 6"	10' - 0"	10' - 0"	8' - 0"	9' - 0"	9' - 0"
500 lb.	6' - 6"	8' - 6"	9' - 6"	5' - 0"	7' - 0"	8' - 6"
Light Duty	8' - 6"	10' - 6"	10' - 6"	8' - 0"	9' - 6"	9' - 6"
Heavy Duty	7' - 0"	8' - 0"	8' - 0"	6' - 0"	7' - 6"	7' - 6"

Note: Above Span Tables are based on a deflection limit of L/80 per Canadian Standards Association (CSA) requirements. Light Duty = 25 psf uniform load plus 250 plf across the plank width at midspan. Heavy Duty = 75 psf uniform load plus 265 plf across the plank width at midspan. Refer to CAN/CSA-S269.2-M87 Standard, Section 5.2.1 for load diagrams.

Contact your representative for more information pertaining to **MASTER PLANK** Laminated Scaffold Boards.

Distributed by:



Roseville, MI 48066

Phone: 586/294-9663 • Fax: 586/294-1505

www.mccauseylumber.com

